

MILANO SUBLIME
EN 14411:2012 Annex G Group Bla UGL

TECHNICAL FEATURE	TEST METHOD	REQUIRED STANDARDS	MILANO SUBLIME
SIZES AND LOOK OF THE TILE	ISO 10545-2	Length and width $\pm 0,6\%/\pm 2.0$ mm Thickness $\pm 5\%/\pm 0.5$ mm Straightness of sides $0,5\%/\pm 1.5$ mm Rectangularity $\pm 0,5\%/\pm 2.0$ mm Surface flatness $\pm 0,5\%/\pm 2.0$ mm Surface quality: 95% of tiles with no defaults	Compliant Compliant Compliant Compliant Compliant
WATER ABSORPTION	ISO 10545-3	≤ 0.5 %	0,09% (average values referred to the last production)
AVERAGE BENDING STRENGTH	ISO 10545-4	35 N/mm ² min.	43,6 N/mm ² (average values referred to the last production)
BREAKING STRENGTH	ISO 10545-4	Thickness $\geq 7,5$ mm: 1300 N min.	Compliant
RESISTANCE TO DEEP ABRASION	ISO 10545-6	175 mm ³ max.	Compliant
FROST RESISTANCE	ISO 10545-12	Required	Compliant
CHEMICAL RESISTANCE (DOMESTIC USE AND SWIMMING POOL CHEMICALS)	ISO 10545-13	min. UB	Compliant

COEFFICIENT OF FRICTION	B.C.R.A. METHOD (D.M. no. 236 of 14/06/1989 of Italian Republic)	Unpolished: DRY: > 0.40 WET: > 0.40
ANTISLIP PROPERTIES	DIN 51130 DIN EN 16165:2021 Annex B	Unpolished: R10
DYNAMIC COEFFICIENT OF FRICTION	DCOF ANSI A326.3	Unpolished: WET: ≥ 0.42

Valid only for items in 1st. choice.

On request we can certify conformity with standards that are not mentioned hereby

The special trims for the series, apart from those used for stair coverings, do not comply with the ISO EN 14411 standard.

Average values refer to tests which have been made on the unpolished surface if not otherwise specifically indicated.

The series highlighted in red have been tested using the new DIN EN 16165:2021, ANSI A326.3 and BS EN 16165:2021 methods.

V3: Tiles with moderate shade and aspect variation.

MILANO SUBLIME gresX2
EN 14411:2012 Annex G Group Bla UGL

TECHNICAL FEATURE	TEST METHOD	REQUIRED STANDARDS	MILANO SUBLIME gresX2
SIZES AND LOOK OF THE TILE	ISO 10545-2	Length and width $\pm 0,6\%/\pm 2.0$ mm Thickness $\pm 5\%/\pm 0.5$ mm Straightness of sides $0,5\%/\pm 1.5$ mm Rectangularity $\pm 0,5\%/\pm 2.0$ mm Surface flatness $\pm 0,5\%/\pm 2.0$ mm Surface quality: 95% of tiles with no defaults	Compliant Compliant Compliant Compliant Compliant
WATER ABSORPTION	ISO 10545-3	≤ 0.5 % (Maximum single value)	< 0,2%
AVERAGE BENDING STRENGTH	ISO 10545-4	35 N/mm ² min. (Single value)	Compliant
	EN 1339	-	T11*
BREAKING STRENGTH	ISO 10545-4	Thickness $\geq 7,5$ mm: 1300 N min.	10.000 N
RESISTANCE TO DEEP ABRASION	ISO 10545-6	175 mm ³ max.	145 mm ³
FROST RESISTANCE	ISO 10545-12	Required	Resistant
CHEMICAL RESISTANCE (DOMESTIC USE AND SWIMMING POOL CHEMICALS)	ISO 10545-13	min. UB	UA Resistant

* Valid only for square formats.

COEFFICIENT OF FRICTION	B.C.R.A. METHOD (D.M. no. 236 of 14/06/1989 of Italian Republic)	Outdoor: DRY: > 0.40 WET: > 0.40
REACTION TO FIRE	EN 13823	A1fl-A1 (no reaction)
ANTISLIP PROPERTIES	DIN 51130 DIN EN 16165:2021 Annex B	Outdoor: R11
ANTISLIP PROPERTIES ON WET SURFACES	DIN 51097 DIN EN 16165:2021 Annex A	Outdoor: A+B

Valid only for items in 1st. choice.

On request we can certify conformity with standards that are not mentioned hereby.

The special trims for the series, apart from those used for stair coverings, do not comply with the ISO EN 14411 standard.

Average values refer to tests which have been made on the unpolished surface if not otherwise specifically indicated.

The series highlighted in red have been tested using the new DIN EN 16165:2021 method.

PRODUCT COMPLIANT WITH LEED® REQUIREMENTS LEADERSHIP IN ENERGY AND ENVIRONMENTAL DESIGN

Ceramiche Coem is a member of the U.S. Green Building Council (USGBC), the American association that takes care of implementing and regulating the construction of sustainable buildings through LEED® certification (Leadership in Energy and Environmental Design).

As a result of their technical and structural characteristics, our products can help buildings obtain a score based on LEED® parameters, and have been duly certified by the external certification body CERTIQUALITY. Our products are compliant with LEED® requisites thanks to their high recyclable material content.

Our products have obtained the EPD (Environmental Product Declaration) for the sector, which provides environmental details on the life cycle of products, in accordance with the international standard ISO 14025, compliant with LEED® requisites.

The light refractive index of the porcelain stoneware support guarantees maximum heat insulation and excellent energy performance. Hygienic and easy to clean, our products help improve the quality and safety of building interiors.

The eco-sustainable requisites do not affect the appearance of the product, and our porcelain stoneware is always on the leading edge of design and technological innovation.

COEM S.p.A.

Cap. Soc. € 12.000.000,00 i.v.
Reg. Impr. di Modena – C.F. 01927780369
R.E.A. Modena n° 252818
P.IVA: IT 01927780369

Sede Amministrativa

42014 Roteglia (RE) – Italy
Via Stradone Secchia, 32
Tel. +39 0536 993111
Fax +39 0536 993248

Sede Legale – Uffici Commerciali

41042 Fiorano Modenese (MO) – Italy
Via Cameazzo, 25
Tel. +39 0536 993111
Fax Comm. Italia +39 0536 993588
Fax Export Dpt. +39 0536 832611



SISTEMI DI
GESTIONE CERTIFICATI
UNI EN ISO 9001:2015
UNI EN ISO 14001:2015
UNI ISO 45001:2023



TROPICAL
TILE & MARBLE

Sustainable sites – Reduction of the heat island effect

Depending on the type of colour and use, the high SRI (Solar Reflectance Index) of Ceramiche Coem products can help reduce the heat island effect (the difference in the thermal gradient between urban and extra-urban areas) and its effects on the microclimate, human habitat and wildlife.

REQUISITES	Credits
OUTDOOR PAVING SR > 33	1 point
LOW SLOPE ROOFS SRI > 82	1 point
HIGH SLOPE ROOFS SRI > 39	1 point

Materials and resources – Declaration and optimisation of construction products

Ceramiche Coem products can help improve LEED® rating in terms of materials and resources.

REQUISITES	Credits
SECTOR EPD	1/2 points
ORIGIN OF RAW MATERIALS – RECYCLED CONTENT	1 point
COMPONENTS – END PRODUCTS AND MATERIALS THAT DO NOT CONTAIN SUBSTANCES CLASSIFIED AS OF VERY HIGH CONCERN ACCORDING TO REACH CRITERIA	1 point

Low-emission materials

Ceramiche Coem products do not emit VOC (Volatile Organic Compounds).

REQUISITES	Credits
PRODUCTS THAT DO NOT CONTAIN VOC	1 point

COEM S.p.A.

Cap. Soc. € 12.000.000,00 i.v.
Reg. Impr. di Modena – C.F. 01927780369
R.E.A. Modena n° 252818
P.IVA: IT 01927780369

Sede Amministrativa

42014 Roteglia (RE) – Italy
Via Stradone Secchia, 32
Tel. +39 0536 993111
Fax +39 0536 993248

Sede Legale – Uffici Commerciali

41042 Fiorano Modenese (MO) – Italy
Via Cameazzo, 25
Tel. +39 0536 993111
Fax Comm. Italia +39 0536 993588
Fax Export Dpt. +39 0536 832611



UNI EN ISO 9001:2015
UNI EN ISO 14001:2015
UNI ISO 45001:2023

